


Topcoat updated to SW 4411 to achieve matte non-slip sheen. PDS and SDS sheets attached in this submittal. Still consistent with SW Deco Quartz system. BB 03/20/25

~~Modify Topcoat from HTS urethane to 4850 Polyaspartic. Modify Grout Coat UVE to more than 16 mils to get desired texture.~~

APPLICATION INFORMATION — SURFACE PREP PROFILE CSP 4-6

VOC MIXED	APPLICATION STEP	MATERIAL	MIXED RATIO	THEORETICAL COVERAGE PER COAT CONCRETE	PACKAGING
<50 g/L	Optional Primer	MPE	2:1	133-160 sq. ft. / gal	3, 15, 165 or 750 gals
<50 g/L 0	1st Broadcast	MPE 5900F	2:1 To excess	133-160 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<50 g/L 0	2nd Broadcast	MPE 5900F	2:1 To excess	65-70 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<100 g/L	Grout Coat	UVE	2:1	107 sq. ft. / gal	3 or 15 gals
<100 g/L	Topcoat	HTS	2:1	535 sq. ft. / gal	Pre-measured kit



~~ALTERNATE SYSTEM #1~~

VOC MIXED	APPLICATION STEP	MATERIAL	MIXED RATIO	THEORETICAL COVERAGE PER COAT CONCRETE	PACKAGING
<50 g/L	Optional Primer	MPE	2:1	133-160 sq. ft. / gal	3, 15, 165 or 750 gals
<50 g/L 0	1st Broadcast	MPE 5900F	2:1 To excess	133-160 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<50 g/L 0	2nd Broadcast	MPE 5900F	2:1 To excess	65-70 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<100 g/L	Grout Coat	UVE	2:1	107 sq. ft. / gal	3 or 15 gals
<100 g/L	Topcoat	UVE	2:1	200 sq. ft. / gal	3 or 15 gals

~~ALTERNATE SYSTEM #2~~

VOC MIXED	APPLICATION STEP	MATERIAL	MIXED RATIO	THEORETICAL COVERAGE PER COAT CONCRETE	PACKAGING
<50 g/L	Optional Primer	MPE	2:1	133-160 sq. ft. / gal	3, 15, 165 or 750 gals
<50 g/L 0	1st Broadcast	MPE 5900F	2:1 To excess	133-160 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<50 g/L 0	2nd Broadcast	MPE 5900F	2:1 To excess	65-70 sq. ft. / gal .4 lbs. / sq. ft.	3, 15, 165 or 750 gals 50 lbs.
<100 g/L	Grout Coat	4850	2:1	125-200 sq. ft. / gal	3 or 15 gals
<100 g/L	Topcoat	4850	2:1	200 sq. ft. / gal	3 or 15 gals

For additional topcoat options, consult the Sherwin-Williams Topcoat Selection Guide or contact your Sherwin Williams representative.